LOW-SHRINK TEXTILE ARTICLES

MADE FROM POLYPROPYLENE FIBERS

Cross Reference to Related Applications

This application is a continuation of co-pending application 09/860,130, filed on

May 17, 2001. This parent application is herein entirely incorporated by reference.

Field of the Invention

This invention relates to improvements in preventing heat- and moisture-shrink

problems in specific polypropylene fibers. Such fibers require the presence of certain

compounds that quickly and effectively provide rigidity to the target polypropylene fiber

after heat-setting. Generally, these compounds include any structure that nucleates

polymer crystals within the target polypropylene after exposure to sufficient heat to melt

the initial pelletized polymer and upon allowing such a melt to cool. The compounds must

nucleate polymer crystals at a higher temperature than the target polypropylene without the

nucleating agent during cooling. In such a manner, the "rigidifying" nucleator compounds

provide nucleation sites for polypropylene crystal growth. After drawing the nucleated

composition into fiber form, the fiber is then exposed to sufficient heat to grow the

crystalline network, thus holding the fiber in a desired position. The preferred

"rigidifying" compounds include dibenzylidene sorbitol based compounds, as well as less

preferred compounds, such as sodium benzoate, certain sodium and lithium phosphate

salts (such as sodium 2,2'-methylene-bis-(4,6-di-tert-butylphenyl)phosphate, otherwise

known as NA-11), and carboxylate salts of cyclic organophosphoric esters (such as NA-

21). Specific methods of manufacture of such fibers, as well as fabric articles made

therefrom, are also encompassed within this invention.

Discussion of the Prior Art

There has been a continued desire to utilize polypropylene fibers in various

different products, ranging from apparel to carpet backings (as well as carpet pile fabrics)

to reinforcement fabrics, and so on. Polypropylene fibers exhibit excellent strength

characteristics, highly desirable hand and feel, and do not easily degrade or erode when

exposed to certain "destructive" chemicals. However, even with such impressive and

beneficial properties and an abundance of polypropylene, which is relatively inexpensive

to manufacture and readily available as a petroleum refinery byproduct, such fibers are not

widely utilized in products that are exposed to relatively high temperatures during use,

cleaning, and the like. This is due primarily to the high and generally non-uniform heat-

and moisture-shrink characteristics exhibited by typical polypropylene fibers. Such fibers

are not heat stable and when exposed to standard temperatures (such as 150°C and 130°C

temperatures), the shrinkage range from about 5% (in boiling water) to about 7-8% (for hot

air exposure) to 12-13% (for higher temperature hot air). These extremely high and varied

shrink rates thus render the utilization and processability of highly desirable polypropylene

fibers very low, particularly for end-uses that require heat stability (such as apparel, carpet

pile, carpet backings, molded pieces, and the like). To date, there has been no simple

solution to such a problem. Some ideas have included narrowing and controlling the

molecular weight distribution of the polypropylene components themselves in each fiber or

2

mechanically working the target fibers prior to and during heat-setting. Unfortunately,

molecular weight control is extremely difficult to accomplish initially, and has only

provided the above-listed shrink rates (which are still too high for widespread utilization

within the fabric industry). Furthermore, the utilization of very high heat-setting

temperatures during mechanical treatment has, in most instances, resulted in the loss of

good hand and feel to the subject fibers. Another solution to this problem is preshrinking

the fibers, which involves winding the fiber on a crushable paper package, allowing the

fiber to sit in the oven and shrink for long times, (crushing the paper package), and then

rewinding on a package acceptable for further processing. This process, while yielding an

acceptable yarn, is expensive, making the resulting fiber uncompetitive as compared to

polyester and nylon fibers. As a result, there has not been any teaching or disclosure

within the pertinent prior art providing any heat- and/or moisture-shrink improvements in

polypropylene fiber technology.

Description of the Invention

It is thus an object of the invention to provide improved shrink rates for standard

polypropylene fibers. A further object of the invention is to provide a class of additives

that, in a range of concentrations, will give low shrinkage. A further object of the

invention is to provide a specific method for the production of nucleator-containing

polypropylene fibers permitting the ultimate production of such low-shrink fabrics

therewith.

Accordingly, this invention encompasses a polypropylene fiber possessing at most

5,000 denier per filament and exhibiting a heat-shrinkage in at least 150°C hot air of at

3

most 11%, wherein said fiber further comprises at least one nucleating agent. Also, this

invention encompasses a polypropylene fiber possessing at most 5,000 denier per filament

and exhibiting a heat-shrinkage in at least 150°C hot air of at most 11%, wherein said fiber

further comprises at least one nucleating agent, and wherein said fiber further exhibits a

long period of at least 20 nm as measured by small-angle x-ray scattering. Furthermore,

this invention encompasses a polypropylene fiber possessing at most 5,000 denier per

filament and comprising at least one nucleating agent, and wherein said fiber further

exhibits a long period of at least 20 nm as measured by small-angle x-ray diffraction

spectroscopy. Additionally, this invention encompasses a polypropylene fiber possessing

at most 5,000 denier per filament and exhibiting a peak crystallization temperature of at

least 115°C as measured by differential scanning calorimetry in accordance with a

modified ASTM Test Method D3417-99 at a cooling rate of 20°C/min, and wherein said

fiber further exhibits a long period of at least 20 nm as measured by small-angle x-ray

scattering. Certain yarns and fabric articles comprising such inventive fibers are also

encompassed within this invention.

Furthermore, this invention also concerns a method of producing such fibers

comprising the sequential steps of a) providing a polypropylene composition in pellet or

liquid form comprising at least 100 ppm by weight of a nucleator compound; b) melting

and mixing said polypropylene composition of step "a" to form a substantially

homogeneous molten plastic formulation; c) extruding said plastic formulation to form a

fiber structure; d) mechanically drawing said extruded fiber (optionally while exposing

said fiber to a temperature of at most 105°C); and e) exposing said drawn fiber of step "d"

to a subsequent heat-setting temperature of at least 110°C. Preferably, step "b" will be

4

performed at a temperature sufficient to effectuate the melting of all polymer constituent

(e.g., polypropylene), and possibly the remaining compounds, including the nucleating

agent, as well (melting of the nucleating agent is not a requirement since some nucleating

agents do not melt upon exposure to such high temperatures). Thus, temperatures within

the range of from about 175 to about 300°C, as an example (preferably from about 200 to

about 275°, and most preferably from about 220 to about 250°C, are proper for this

purpose. The extrusion step ("c") should be performed while exposing the polypropylene

formulation to a temperature of from about 185 to about 300°C, preferably from about 210

to about 275°C, and most preferably from about 230 to about 250°C, basically sufficient

to perform the extrusion of a liquefied polymer without permitting breaking of any of the

fibers themselves during such an extrusion procedure. The drawing step may be

performed at a temperature which is cooler than normal for a standard polypropylene (or

other polymer) fiber drawing process. Thus, if a cold-drawing step is followed, such a

temperature should be below about 105°C, more preferably below about 100 °C, and most

preferably below about 90°C. Of course, higher temperatures may be used if no such cold

drawing step is followed. The final heat-setting temperature is necessary to "lock" the

polypropylene crystalline structure in place after extruding and drawing. Such a heat-

setting step generally lasts for a portion of a second, up to potentially a couple of minutes

(i.e., from about 1/10th of a second, preferably about ½ of a second, up to about 3 minutes,

preferably greater than ½ of a second). The heat-setting temperature must be greater than

the drawing temperature and must be at least 110°C, more preferably at least about 115°,

and most preferably at least about 125°C. The term "mechanically drawing" is intended to

encompass any number of procedures which basically involve placing an extensional force

on fibers in order to elongate the polymer therein. Such a procedure may be accomplished

with any number of apparatus, including, without limitation, godet rolls, nip rolls, steam

cans, hot or cold gaseous jets (air or steam), and other like mechanical means.

In another embodiment of the method of making such inventive fibers, step "c"

noted above may be further separated into two distinct steps. A first during which the

polymer is extruded as a sheet or tube, and a second during which the sheet or tube is slit

into narrow fibers of less than 5000 deniers per filament (dpf).

All shrinkage values discussed as they pertain to the inventive fibers and methods

of making thereof correspond to exposure times for each test (hot air and boiling water) of

about 5 minutes. The heat-shrinkage at about 150°C in hot air is, as noted above, at most

11% for the inventive fiber; preferably, this heat-shrinkage is at most 9%; more preferably

at most 8%; and most preferably at most 7%. Also, the amount of nucleating agent present

within the inventive fiber is at least 10 ppm; preferably this amount is at least 100 ppm;

and most preferably is at least 1250 ppm. Any amount of such a nucleating agent should

suffice to provide the desired shrinkage rates after heat-setting of the fiber itself; however,

excessive amounts (e.g., above about 10,000 ppm and even as low as about 6,000 ppm)

should be avoided, primarily due to costs, but also due to potential processing problems

with greater amounts of additives present within the target fibers.

The term "polypropylene" is intended to encompass any polymeric composition

comprising propylene monomers, either alone or in mixture or copolymer with other

randomly selected and oriented polyolefins, dienes, or other monomers (such as ethylene,

butylene, and the like). Such a term also encompasses any different configuration and

arrangement of the constituent monomers (such as syndiotactic, isotactic, and the like).

6

Thus, the term as applied to fibers is intended to encompass actual long strands, tapes, threads, and the like, of drawn polymer. The polypropylene may be of any standard melt flow (by testing); however, standard fiber grade polypropylene resins possess ranges of Melt Flow Indices between about 2 and 50. Contrary to standard plaques, containers, sheets, and the like (such as taught within U.S. Pat. No. 4,016,118 to Hamada et al., for example), fibers clearly differ in structure since they must exhibit a length that far exceeds its cross-sectional area (such, for example, its diameter for round fibers). Fibers are extruded and drawn; articles are blow-molded or injection molded, to name two alternative production methods. Also, the crystalline morphology of polypropylene within fibers is different than that of standard articles, plaques, sheets, and the like. For instance, the dpf of such polypropylene fibers is at most about 5000; whereas the dpf of these other articles is much greater. Polypropylene articles generally exhibit spherulitic crystals while fibers exhibit elongated, extended crystal structures. Thus, there is a great difference in structure between fibers and polypropylene articles such that any predictions made for spherulitic particles (crystals) of nucleated polypropylene do not provide any basis for determining the effectiveness of such nucleators as additives within polypropylene fibers.

Another class of nucleating agents, alluded to above, was suggested by Nakahara et al. in U.S. Pat. No. 4,463,113, in which cyclic bis-phenol phosphates was disclosed as nucleating and clarifying agents for polyolefin resins. Kimura et al. then suggests in U.S. Pat. No. 5,342,868 that the addition of an alkali metal carboxylate to basic polyvalent metal salt of cyclic organophosphoric ester can further improve the clarification effects of such additives. Compounds that are based upon these technologies are marketed under the trade name NA-11 and NA-21, respectively, by Asahi Denka, again as mentioned above.

7

The terms "nucleators", "nucleator compound(s)", "nucleating agent", and "nucleating agents" are intended to generally encompass, singularly or in combination, any additive to polypropylene that produces nucleation sites for polypropylene crystals from transition from its molten state to a solid, cooled structure. Hence, since the polypropylene composition (including nucleator compounds) must be molten to eventually extrude the fiber itself, the nucleator compound will provide such nucleation sites upon cooling of the polypropylene from its molten state. The only way in which such compounds provide the necessary nucleation sites is if such sites form prior to polypropylene recrystallization itself. Thus, any compound that exhibits such a beneficial effect and property is included within this definition. Such nucleator compounds more specifically include dibenzylidene sorbitol types, including, without limitation, dibenzylidene sorbitol (DBS), mono-methyldibenzylidene sorbitol, such as 1,3:2,4-bis(p-methylbenzylidene) sorbitol (p-MDBS), dimethyl dibenzylidene sorbitol, such as 1,3:2,4-bis(3,4-dimethylbenzylidene) sorbitol (3,4-DMDBS); other compounds of this type include, again, without limitation, sodium benzoate, NA-11, and the like. The concentration of such nucleating agents (in total) within the target polypropylene fiber is at least 100 ppm, preferably at least 1250 ppm. Thus, from about 100 to about 5000 ppm, preferably from about 500 ppm to about 4000 ppm, more preferably from about 1000 ppm to about 3500 ppm, still more preferably from about 1500 ppm to about 3000 ppm, even more preferably from about 2000 ppm to about 3000 ppm, and most preferably from about 2500 to about 3000 ppm. Furthermore, fibers may be produced by the extrusion and drawing of a single strand of polypropylene as described above, or also by extrusion of a sheet, then cutting the sheet into fibers, then

following the steps as described above to draw, heat-set, and collect the resultant fibers. In

addition, other methods to make fibers, such as fibrillation, and the like, are envisioned for

the same purpose.

Also, without being limited by any specific scientific theory, it appears that the

shrink-reducing nucleators which perform the best are those which exhibit relatively high

solubility within the propylene itself. Thus, compounds which are readily soluble, such as

1,3:2,4-bis(p-methylbenzylidene) sorbitol provides the lowest shrinkage rate for the

desired polypropylene fibers. The DBS derivative compounds are considered the best

shrink-reducing nucleators within this invention due to the low crystalline sizes produced

by such compounds. Other nucleators, such as NA-11, also provide good low-shrink

characteristics to the target polypropylene fiber; however, apparently due to poor

dispersion of NA-11 in polypropylene and the large and varied crystal sizes of NA-11

within the fiber itself, the shrink rates are noticeably higher than for the highly soluble, low

crystal-size polypropylene produced by well-dispersed MDBS.

One manner of testing for the presence of a nucleating agent within the target fibers

is preferably through differential scanning calorimetry to determine the peak crystallization

temperature exhibited by the resultant polypropylene. The fiber is melted and placed

between two plates under high temperature and pressure to form a sheet of sample plastic.

A sample of this plastic is then melted and subjected to a differential scanning calorimetry

analytical procedure in accordance with modified ASTM Test Method D3417-99 at a

cooling rate of 20°C/minute. A sufficiently high peak crystallization temperature (above

about 115°C, more preferably above about 116°C, and most preferably above about

116.5°C), well above that exhibited by the unnucleated polypropylene itself, shall indicate

the presence of a nucleating agent since attaining such a high peak crystallization without a

nucleating agent is not generally possible.

It has been determined that the nucleator compounds that exhibit good solubility in

the target molten polypropylene resins (and thus are liquid in nature during that stage in

the fiber-production process) provide more effective low-shrink characteristics. Thus, low

substituted DBS compounds (including DBS, p-MDBS) appear to provide fewer

manufacturing issues as well as lower shrink properties within the finished polypropylene

fibers themselves. Although p-MDBS is preferred, however, any of the above-mentioned

nucleators may be utilized within this invention as long as the long period (SAXS)

measurements are met or the low shrink requirements are achieved through utilization of

such compounds. Mixtures of such nucleators may also be used during processing in order

to provide such low-shrink properties as well as possible organoleptic improvements,

facilitation of processing, or cost.

In addition to those compounds noted above, sodium benzoate and NA-11 are well

known as nucleating agents for standard polypropylene compositions (such as the

aforementioned plaques, containers, films, sheets, and the like) and exhibit excellent

recrystallization temperatures and very quick injection molding cycle times for those

purposes. The dibenzylidene sorbitol types exhibit the same types of properties as well as

excellent clarity within such standard polypropylene forms (plaques, sheets, etc.). For the

purposes of this invention, it has been found that the dibenzylidene sorbitol types are

preferred as nucleator compounds within the target polypropylene fibers. Of interest, as

well, is the ability to provide a purely liquid formulation of the dibenzylidene sorbitol

compounds for introduction within the target polypropylene compositions. Such liquid

10

DBS formulations comprise certain nonionic surfactants that can be selected both for their liquefying and stability-providing benefits to the DBS compounds themselves, but also potentially for their lubricating properties for the eventual fiber. In such a manner, the amount of lubricant generally required for and added to the target fiber may be reduced or eliminated, thus reducing costs associated with such additives. Thus, the surfactants required for such a liquid nucleator composition of 3,4-DMDBS (or other types of nucleating agents), include those which are nonionic and which are ethoxylated to the extent that their hydrophilic-lipophilic balance (HLB) is greater than about 8.5. HLB is a measure of the solubility of a surfactant both in oil and in water and is approximated as one-fifth (1/5) the weight percent of ethoxy groups present on the particular surfactant backbone. More specifically, such surfactants exhibit a HLB value of more preferably greater than about 12, and most preferably greater than about 13, and must possess at least some degree of ethoxylation, more preferably greater than about 4 molar equivalents of ethylene oxide (EO) per molecule, and most preferably greater than about 9.5 molar equivalents of EO per molecule.

Of these preferred surfactants, the most preferred for utilization within the potential fluid nucleating agent dispersion for purposes of this invention include, in tabulated form:

11

SURFACTANT TABLE
Preferred Diluent Surfactants (with Tradenames)

Ex.	Surfactant	Available as and From	HLB #
1	sorbitan monooleate (20 EO)	Tween 80®; Imperial Chemical (ICI)	15.0
2	sorbitan monostearate (20 EO)	Tween 60®; ICI	14.9
3	sorbitan monopalmitate (20 EO)	Tween 40®; ICI	15.6
4	sorbitan monolaurate (20 EO)	Tween 20®; ICI	16.7
5	dinonylphenol ether (7 EO)	Igepal® DM 430; Rhône-Poulenc (RP)	9.5
6	nonylphenol ether (6 EO)	Igepal® CO 530; RP	10.8
7	nonylphenol ether (12 EO)	Igepal® CO 720; RP	14.2
8	dinonylphenol ether (9 EO)	Igepal® DM 530; RP	10.6
9	nonylphenol ether (9 EO)	Igepal® CO 630; RP	13.0
10	nonylphenol ether (4 EO)	Igepal® CO 430; RP	8.8
11	dodecylphenol ether (5.5 EO)	Igepal® RC 520; RP 430	9.6
12	dodecylphenol ether (9.5 EO)	Igepal® RC 620; RP	12.3
13	dodecylphenol ether (11 EO)	Igepal® RC 630; RP	13.0
14	nonylphenol ether (9.5 EO)	Syn Fac® 905; Milliken & Company	~13
15	octylphenol ether (10 EO)	Triton® X-100; Rohm & Haas	13.5

This list is not exhaustive as these are merely the preferred surfactants for use within the potential fluid nucleating agent dispersion for utilization within this invention. In such a fluid dispersion, then, the nucleating agent, such as preferably 3,4-DMDBS, comprises at most 40% by weight, preferably about 30% by weight, of the entire inventive fluid dispersion. Any higher amount will deleteriously affect the viscosity of the dispersion. Preferably the amount of surfactant is from about 70% to about 99.9%, more preferably from about 70% to about 85%; and most preferably, from about 70% to about 75% of the entire inventive fluid dispersion. A certain amount of water may also be present in order to effectively lower the viscosity of the overall liquid dispersion. Optional additives may include plasticizers, antistatic agents, stabilizers, ultraviolet absorbers, and other similar standard polyolefin thermoplastic additives. Other additives may also be present within this composition, most notably antioxidants, antistatic compounds, perfumes, chlorine scavengers, and the like. As noted above, this type of fluid dispersion

is disclosed in greater detail within U.S. Pat. Nos. 6,102,999 and 6,127,440, both herein

entirely incorporated by reference. Most preferred is a composition of 30% by weight of

3,4-DMDBS and 70% by weight of Tween® 80. This mixture is listed in the Preferred

Embodiments section below as "Liquid 3,4-DMDBS".

The closest prior art references teach the addition of nucleator compounds to

general polypropylene compositions (such as in U.S. Pat. No. 4,016,118, referenced

above). However, some teachings include the utilization of certain DBS compounds

within limited portions of fibers in a multicomponent polypropylene textile structure. For

example, U.S. Patent Nos. 5,798,167 to Connor et al. and 5,811,045 to Pike, both teach the

addition of DBS compounds to polypropylene in fiber form; however, there are vital

differences between those disclosures and the present invention. For example, both

patents require the aforementioned multicomponent structures of fibers. Thus, even with

DBS compounds in some polypropylene fiber components within each fiber type, the

shrink rate for each is dominated by the other polypropylene fiber components which do

not have the benefit of the nucleating agent. Also, there are no lamellae that give a long

period (as measured by small-angle X-ray scattering) thicker than 20 nm formed within the

polypropylene fibers due to the lack of a post-heatsetting step being performed. Again,

these thick lamellae provide the desired inventive higher heat-shrink fiber. Also of

importance is the fact that, for instance, Connor et al. require a nonwoven polypropylene

fabric laminate containing a DBS additive situated around a polypropylene internal fabric

layer which contained no nucleating agent additive. The internal layer, being

polypropylene without the aid of a nucleating agent additive, dictates the shrink rate for

this structure. Furthermore, the patentees do not expose their yarns and fibers to heat-

13

setting procedures in order to permanently configure the crystalline fiber structures of the

yarns themselves as low-shrink is not their objective.

In addition, Spruiell, et al, Journal of Applied Polymer Science, Vol. 62, pp. 1965-

75 (1996), reveal using a nucleating agent, MDBS, at 0.1%, to increase the nucleation rate

during spinning. However, after crystallizing and drawing the fiber, Spruiell et al. do not

expose the nucleated fiber to any heat, which is necessary to impart the very best shrinkage

properties, therefore the shrinkage of their fibers was similar to conventional

polypropylene fibers without a nucleating agent additive. In the examples below, yarn

made with similar levels of nucleating agent additives included and no further heat

exposure showed worse shrinkage (at all measured temperatures after the standard 5

minute exposure time) than commercial fibers, and fibers which contained no

additive and were exposed to the same conditions. Thus, in addition to the presence of the

nucleating agent additive, exposure to heat after mechanical drawing is a crucial step in the

invention.

Of particular interest and which has been determined to be of primary importance

in the production of such inventive low-shrink polypropylene fibers, is the discovery that,

at the very least, the presence of nucleating agent within heat-set polypropylene fibers (as

discussed herein), provides high long period measurements for the crystalline lamellae of

the polypropylene itself. This discovery is best explained by the following:

Polymers, when crystallized from a melt under dynamic temperature and stress

conditions, first supercool and then crystallize with the crystallization rate dependent on

the number of nucleation sites, and the growth rate of the polymer, which are both in turn

related to the thermal and mechanical working that the polymer is subjected to as it cools.

14

These processes are particularly complex in a normal fiber drawing line. The results of this complex crystallization, however, can be measured using small angle x-ray scattering (SAXS), with the measured SAXS long period representative of an average crystallization temperature. A higher SAXS long period corresponds to thicker lamellae (which are the plate-like polymer crystals characteristic of semi-crystalline polymers like PP). The higher the crystallization temperature of the average crystal, the thicker the measured SAXS long period will be. Further, higher SAXS long periods are characteristic of more thermally stable polymeric crystals. Crystals with shorter SAXS long periods will "melt", or relax and recrystallize into new, thicker crystals, at a lower temperature than those with higher SAXS long periods. Crystals with higher SAXS long periods remain stable to higher temperatures, requiring more heat to destabilize the crystalline structure.

In highly oriented polymeric samples such as fibers, those with higher SAXS long periods will remain stable to higher temperatures. Thus the shrinkage, which is a normal effect of the relaxation of the highly oriented polymeric samples, remains low to higher temperatures than in those highly oriented polymeric samples with lower SAXS long periods. In this invention, as is evident from these measurements, the nucleating additive is used in conjunction with a thermal treatment to create fibers with extremely high SAXS long periods of at least 20 nm, or preferably at least 22 nm, which in turn are very stable and exhibit low shrinkage up to very high temperatures.

Furthermore, such fibers may also be colored to provide other aesthetic features for the end user. Thus, the fibers may also comprise coloring agents, such as, for example, pigments, with fixing agents for lightfastness purposes. For this reason, it is desirable to utilize nucleating agents that do not impart visible color or colors to the target fibers.

15

Other additives may also be present, including antistatic agents, brightening compounds,

clarifying agents, antioxidants, antimicrobials (preferably silver-based ion-exchange

compounds, such as ALPHASAN® antimicrobials available from Milliken & Company),

UV stabilizers, fillers, and the like. Furthermore, any fabrics made from such inventive

fibers may be, without limitation, woven, knit, non-woven, in-laid scrim, any combination

thereof, and the like. Additionally, such fabrics may include fibers other than the inventive

polypropylene fibers, including, without limitation, natural fibers, such as cotton, wool,

abaca, hemp, ramie, and the like; synthetic fibers, such as polyesters, polyamides,

polyaramids, other polyolefins (including non-low-shrink polypropylene), polylactic acids,

and the like; inorganic fibers such as glass, boron-containing fibers, and the like; and any

blends thereof.

Brief Description of the Drawings

The accompanying drawings, which are incorporated in and constitute a part of this

specification, illustrate a potentially preferred embodiment of producing the inventive low-

shrink polypropylene fibers and together with the description serve to explain the

principles of the invention wherein:

FIG. 1 is a schematic of the potentially preferred method of producing low-shrink

polypropylene.

FIGURE 2 is described in greater detail below with regard to small angle X-ray

scattering and is a graphical representation of the integrated intensity data I(q) as a   ·

function of 2θ in order to determine the long period spacing of the target fibers.

16

FIGURE 3 is also described in greater detail below with regard to small angle X-ray scattering and is a graphical representation of the K(z) function to aid in the ultimate determination of long period spacing.

Detailed Description of the Drawing and of the Preferred Embodiment

FIG. 1 depicts the non-limiting preferred procedure followed in producing the inventive low-shrink polypropylene fibers. The entire fiber production assembly 10 comprises an extruder 11 comprising four different zones 12, 14, 16, 18 through which the polymer (not illustrated) passes at different, increasing temperatures. The molten polymer is mixed with the nucleator compound (also molten) within a mixer zone 20. Basically, the polymer (not illustrated) is introduced within the fiber production assembly 10, in particular within the extruder 11. The temperatures, as noted above, of the individual extruder zones 12, 14, 16, 18 and the mixing zone 20 are as follows: first extruder zone 12 at 205°C, second extruder zone 14 at 215°C, third extruder zone 16 at 225°C, fourth extruder zone 18 at 235°C, and mixing zone 20 at 245°C. The molten polymer (not illustrated) then moves into a spin head area 22 set at a temperature of 250°C which is then moved into the spinneret 24 (also set at a temperature of 250°C) for strand extrusion. The fibrous strands 28 then pass through a heated shroud 26 having an exposure temperature of 180°C. The speed at which the polymer strands (not illustrated) pass through the extruder 11, spin pack 22, and spinneret 24 is relatively slow until the fibrous strands 28 are pulled through by the draw rolls 32, 34, 38. The fibrous strands 28 extend in length due to a greater pulling speed in excess of the initial extrusion speed within the extruder 11. The fibrous strands 28 are thus collected after such extension by a take-up roll 32 (set at a

17

speed of 370 meters per minute) into a larger bundle **30** which is drawn by the

aforementioned draw rolls **34, 38** into a single yarn **33**. The draw rolls are heated to a very

low level as follows: first draw roll **34** 68°C and second draw roll **38** 88°C, as compared

with the remaining areas of high temperature exposure as well as comparative fiber

drawing processes. The first draw roll **34** rotates at a speed of about 377 meters per

minute and is able to hold fifteen wraps of the polypropylene fiber **33** through the

utilization of a casting angle between the draw roll **34** and the idle roll **36**. The second

draw roll **38** rotates at a higher speed of about 785 meters per minute and holds eight

wraps of fiber **33**, and thus requires its own idle roll **40**. After drawing by these cold

temperature rolls **34, 38**, the fiber is then heat-set by a combination of two different heat-

set rolls **42, 44** configured in a return scheme such that eighteen wraps of fiber **33** are

permitted to reside on the rolls **42, 44** at any one time. The time of such heat-setting is

very low due to a low amount of time in contact with either of the actual rolls **42, 44**, so a

total time of about 0.5 seconds is standard. The temperatures of such rolls **42, 44** are

varied below to determine the best overall temperature selection for such a purpose. The

speed of the combination of rolls **42, 44** is about 1290 meters per minute. The fiber **33**

then moves to a relax roll **46** holding up to eight wraps of fiber **33** and thus also having its

own feed roll **48**. The speed of the relax roll **46** is lower than the heat-set roll (1280

meters per minute) in order to release some tension on the heat-set fiber **33**. From there,

the fiber **33** moves to a winder **50** and is placed on a spool (not illustrated).

Inventive Fiber and Yarn Production

The following non-limiting examples are indicative of the preferred embodiment of this invention:

Yarn Production

Yarn was made by compounding Amoco 7550 fiber grade polypropylene resin (melt flow of 18) with a nucleator additive and a standard polymer stabilization package consisting of 500 ppm of Irganox® 1010, 1000 ppm of Irgafos® 168 (both antioxidants available from Ciba), and 800 ppm of calcium stearate. The base mixture was compounded at 2500 ppm in a twin screw extruder (at 220°C in all zones) and made into pellets. The additive was selected from the group of three polypropylene clarifiers commercially available from Milliken & Company, Millad® 3905 (DBS), Millad® 3940 (p-MDBS sorbitol), Millad® 3988 (3,4-DMDBS), two polypropylene nucleators commercially available from Asahi-Denka Chemical Company (NA-11 and NA-21), sodium benzoate, Liquid 3,4-DMDBS, and 1,3:2,4-bis(2,4,5-trimethylbenzylidene) sorbitol (2,4,5-TMDBS).

The pellets were then fed into the extruder on an Alex James & Associates fiber extrusion line as noted above in **FIG. 1**. Yarn was spun with the extrusion line conditions shown in Table 1 using a 68 hole spinneret, giving a yarn of nominally 150 denier. For each additive, four yarns were spun with heat-set temperatures of 100°, 110°, 120°, and 130°C respectively. These temperatures are the set temperatures for the controller for the rolls **42, 44**. In practice, a variation is found to exist over the surface of the rolls **42, 44**, up to as much as 10°C. Pellets with no nucleator additive were used to make control fibers.

19

The yarns were tested for shrinkage in boiling water by cutting a length of yarn, marking the ends of a 10" section with tape, placing the yarn in boiling water for 5 minutes, then taking the yarn out and measuring the length of the section between the tape marks. Measurements were taken on five pieces of each yarn, and the average change in dimension is divided by the initial length (10 inches) to give % shrinkage. Also, the measurements below have a statistical error of +/- 0.4 percentage units.

The yarns were similarly tested for shrinkage in hot air at 150°C and 130°C by marking a 10" section of yarn, placing it in an oven for five minutes at the measurement temperature, and similarly measuring the % shrinkage after removing the yarn from the oven. Again, five samples were measured, and the average shrinkage results are reported for each sample in Table 1. The shrink measurements are listed below the tested nucleators for each yarn sample. The yarn samples were as follows:

POLYPROPYLENE YARN COMPOSITION TABLE
Yarn Samples with Specific Nucleators Added

Yarn Sample	Nucleator Added
A	NA-11
B	NA-21
C	Sodium Benzoate
D	DBS
E	p-MDBS
F	3,4-DMDBS
G	Liquid 3,4-DMDBS
H	2,4,5-TMDBS
I(Comparative)	None (Control)

20

Fiber and Yarn Physical Analyses

These sample yarns were then tested for shrink characteristics with a number of

different variables including heat-set temperatures differences (on the heat-set rolls) during

manufacture and different heat-exposure conditions (hot air at various temperatures and

boiling water exposure at temperatures in excess of 100°C). The results are tabulated

below:

EXPERIMENTAL TABLE 1
Experimental Shrink Measurements for Sample Yarns

Sample Yarn	Heatset Temp.(°C)	Shrinkage Test and Temp. .(°C)	Shrinkage
A	100	150 Hot air	9.5%
A	110	150 Hot air	9.4%
A	120	150 Hot air	8.1%
A	130	150 Hot air	6.7%
A	100	130 Hot air	7.4%
A	110	130 Hot air	5.9%
A	120	130 Hot air	4.9%
A	130	130 Hot air	4.0%
A	100	Boiling water	4.9%
A	110	Boiling water	4.1%
A	120	Boiling water	3.6%
A	130	Boiling water	2.7%
B	100	150 Hot air	11.1%
B	110	150 Hot air	10.1%
B	120	150 Hot air	9.3%
B	130	150 Hot air	6.7%
B	100	130 Hot air	8.1%
B	110	130 Hot air	7.3%
B	120	130 Hot air	6.3%
B	130	130 Hot air	3.4%
B	100	Boiling water	5.6%
B	110	Boiling water	4.7%
B	120	Boiling water	2.7%
B	130	Boiling water	2.3%
C	100	150 Hot air	10.9%
C	110	150 Hot air	11.2%
C	120	150 Hot air	9.5%
C	130	150 Hot air	7.1%
C	100	130 Hot air	7.8%

21

C	110	130 Hot air	7.4%
C	120	130 Hot air	6.2%
C	130	130 Hot air	4.5%
C	100	Boiling water	6.0%
C	110	Boiling water	5.0%
C	120	Boiling water	3.9%
C	130	Boiling water	2.6%
D	100	150 Hot air	9.8%
D	110	150 Hot air	9.7%
D	120	150 Hot air	9.5%
D	130	150 Hot air	5.8%
D	100	130 Hot air	7.4%
D	110	130 Hot air	6.9%
D	120	130 Hot air	6.2%
D	130	130 Hot air	2.9%
D	100	Boiling water	5.6%
D	110	Boiling water	4.5%
D	120	Boiling water	3.1%
D	130	Boiling water	2.1%
E	100	150 Hot air	10.9%
E	110	150 Hot air	9.2%
E	120	150 Hot air	8.0%
E	130	150 Hot air	4.0%
E	100	130 Hot air	7.5%
E	110	130 Hot air	6.1%
E	120	130 Hot air	4.5%
E	130	130 Hot air	2.7%
E	100	Boiling water	4.6%
E	110	Boiling water	4.0%
E	120	Boiling water	2.4%
E	130	Boiling water	1.9%
F	100	150 Hot air	13.6%
F	110	150 Hot air	12.4%
F	120	150 Hot air	7.3%
F	130	150 Hot air	7.2%
F	100	130 Hot air	9.2%
F	110	130 Hot air	8.0%
F	120	130 Hot air	3.7%
F	130	130 Hot air	3.4%
F	100	Boiling water	6.5%
F	110	Boiling water	4.0%
F	120	Boiling water	2.6%
F	130	Boiling water	2.7%
G	100	150 Hot air	12.9%
G	110	150 Hot air	11.7%
G	120	150 Hot air	9.3%

G	130	150 Hot air	7.6%
G	100	130 Hot air	9.2%
G	110	130 Hot air	8.8%
G	120	130 Hot air	6.5%
G	130	130 Hot air	4.3%
G	100	Boiling water	6.0%
G	110	Boiling water	5.3%
G	120	Boiling water	3.9%
G	130	Boiling water	2.8%
H	100	150 Hot air	12.2%
H	110	150 Hot air	10.9%
H	120	150 Hot air	9.6%
H	130	150 Hot air	6.8%
H	100	130 Hot air	8.9%
H	110	130 Hot air	8.0%
H	120	130 Hot air	6.3%
H	130	130 Hot air	3.0%
H	100	Boiling water	5.5%
H	110	Boiling water	4.7%
H	120	Boiling water	3.3%
H	130	Boiling water	2.1%
I	100	150 Hot air	21.3%
I	110	150 Hot air	19.3%
I	120	150 Hot air	17.4%
I	130	150 Hot air	13.4%
I	100	130 Hot air	12.5%
I	110	130 Hot air	10.7%
I	120	130 Hot air	8.6%
I	130	130 Hot air	5.3%
I	100	Boiling water	6.8%
I	110	Boiling water	5.2%
I	120	Boiling water	3.2%
I	130	Boiling water	3.2%

In addition, two commercial yarns were obtained from Filament Fiber Technology and tested in each of the three tests, with the results shown in Table 3. Commercial Yarn #1 is an air jet textured yarn with a black pigment. Commercial Yarn #2 is an air jet textured yarn with a white pigment.

EXPERIMENTAL TABLE 2
Experimental Data for Comparative Commercial Polypropylene Yarns

Test	Comm. Yarn #1	Comm. Yarn #2
150°C Hot air shrinkage	13.0%	12.1%
130°C Hot air shrinkage	7.8%	7.0%
Boiling water shrinkage	4.8%	5.5%

It is evident from these two TABLEs that the inventive polypropylene yarns (including those made from the inventive method described above) exhibit vastly improved shrinkage rates for all three test methods and thus are clearly improvements over the commercially available prior art yarns as well as those yarns lacking nucleating agent and heat-set.

Additive Level Dependence

To test the dependence on nucleator additive level, additional yarns were spun in accordance with the method described above with varying levels of additive using Amoco 7550 resin. The additive was compounded into the resin and the fibers spun under the same conditions as in the previous examples. The yarns were similarly tested, with the results shown in Table 5.

POLYPROPYLENE YARN SAMPLE TABLE
Yarn Samples with Specific Nucleators Added

Yarn Sample	Nucleator Added (Amount ppm)
J	NA-11 (1000)
K	3,4-DMDBS (1250)
L	2,4,5-TMDBS (1250)

24

EXPERIMENTAL TABLE 3

Experimental Data for Different Nucleator Levels in Polypropylene Yarns

Sample Yarn	Heatset Temp.(°C)	Shrinkage Test and Temp. .(°C)	Shrinkage
J	100	150 Hot air	18.1%
J	110	150 Hot air	16.6%
J	120	150 Hot air	16.7%
J	130	150 Hot air	9.0%
J	100	130 Hot air	10.4%
J	110	130 Hot air	9.0%
J	120	130 Hot air	6.8%
J	130	130 Hot air	4.5%
J	100	Boiling water	5.4%
J	110	Boiling water	4.8%
J	120	Boiling water	3.3%
J	130	Boiling water	2.6%
K	100	150 Hot air	15.7%
K	110	150 Hot air	17.1%
K	120	150 Hot air	13.0%
K	130	150 Hot air	8.8%
K	100	130 Hot air	9.3%
K	110	130 Hot air	8.6%
K	120	130 Hot air	5.5%
K	130	130 Hot air	4.0%
K	100	Boiling water	6.8%
K	110	Boiling water	4.5%
K	120	Boiling water	3.3%
K	130	Boiling water	2.5%
L	100	150 Hot air	16.9%
L	110	150 Hot air	15.8%
L	120	150 Hot air	13.2%
L	130	150 Hot air	8.7%
L	100	130 Hot air	11.1%
L	110	130 Hot air	9.2%
L	120	130 Hot air	6.8%
L	130	130 Hot air	4.5%
L	100	Boiling water	6.8%
L	110	Boiling water	4.3%
L	120	Boiling water	3.3%
L	130	Boiling water	2.3%

Thus, additive levels are important to providing overall good low shrinkage characteristics for the target polypropylene yarns. Higher levels appear to provide better shrinkage properties.

X-ray Scattering Analysis

The long period spacing of several of the above yarns was tested by small angle x-ray scattering (SAXS). The small angle x-ray scattering data was collected on a Bruker AXS (Madison, WI) Hi-Star multi-wire detector placed at a distance of 105 cm from the sample in an Anton-Paar vacuum chamber where the chamber was evacuated to a pressure of not more than 100 mTorr. X-rays (λ = 1.54178 Å) were generated with a MacScience rotating anode (40 kV, 40 mA) and focused through three pinholes to a size of 0.2 mm. The entire system (generator, detector, beampath, sample holder, and software) is commercially available as a single unit from Bruker AXS. The detector was calibrated per manufacturer recommendation using a sample of silver behenate.

A typical data collection was conducted as follows. To prepare the sample, the yarn was wrapped around a 3 mm brass tube with a 2 mm hole drilled in it, and then the tube was placed in an Anton-Paar vacuum sample chamber on the x-ray equipment such that the yarn was exposed to the x-ray beam through the hole. The path length of the x-ray beam through the sample was between 2-3 mm. The sample chamber and beam path was evacuated to less than 100 mTorr and the sample was exposed to the X-ray beam for one hour. Two-dimensional data frames were collected by the detector and unwarped automatically by the system software. The data were smoothed within the system software using a 2-pixel convolution prior to integration. To obtain the intensity scattering data [I(q)] as a function of scattering angle [2θ] the data were integrated over ϕ with the

26

manufacturer's software set to give a 2θ range of 0.2° - 2.5° in increments of 0.01° using

the method of bin summation. These raw scattering data were then transformed into a real

space correlation function K(z) using a FORTRAN program written in house to evaluate

the integral:

$$K(z) = \int_0^\infty 4\pi q^2 \ I(q) \cos(2\pi qz) \ dq \quad \text{where} \quad q = 4\pi \sin(\theta)/\lambda \ .$$

The integral was evaluated by direct summation over all values 2ϑ in the data range (0.2°

- 2.5°) and over the real space values from 0 nm – 50 nm. This follows the method of G.

Strobl (Strobl G. *The Physics of Polymers*; Springer: Berlin 1997, pp. 408-14), entirely

incorporated by reference. From the one-dimensional correlation function, K(z), one can

extract the morphological data of interest, in this case long period spacing (L). The

integrated intensity data I(q) as a function of 2θ demonstrates a broad hump corresponding

to the long period spacing (Figure 2). The K(z) function has a characteristic shape (Figure

3). The relevant extractable data points are indicated. Long-period spacing is extracted

from K(z) data as the global maximum of the function occurring at a higher z value than

the global minimum.

These data are collected in Table 6. Also included in Table 6 are the measurements

as a result of 150°C hot air exposure (to test for shrinkage). As can be clearly seen, a

longer SAXS long period corresponds to a lower shrinkage. In addition, samples prepared

with the additive, but without sufficient heat in the process (represented in this case by a

130°C heatset), gave a smaller SAXS long period and a correspondingly higher 150°C hot

air shrinkage. The following TABLE thus shows the correlation between SAXS long

period measurements with 150°C hot air exposure (for shrinkage of the target yarns), as

well as the correlation between heat-set temperatures with such characteristics.

EXPERIMENTAL TABLE 4
SAXS and 150°C Hot Air Shrinkage Data For Yarn Samples

Sample Yarn	Heat-set Temp. (°C)	Shrinkage	SAXS Long Period
A	130	6.7%	26.45
B	130	6.7%	22.35
C	130	7.1%	21
D	130	5.8%	23.2
E	130	4.0%	26.4
E	120	8.0%	21
E	110	9.2%	18.4
F	130	7.2%	21.55
H	130	6.8%	22.4
Comm. Yarn 1------		12.1%	16.95
Comm. Yarn 2------		13.0%	15.6

It is thus evident that the higher the long period as measured by small-angle X-ray scattering, the lower the shrinkage exhibited by the target polypropylene yarn.

Peak Crystallization Temperatures

As noted above, in order to provide the desired low-shrink characteristics to the target yarns and/or fibers, a nucleating agent should be added. Although the presence of a nucleating agent or agents is necessary to accord such low-shrink properties in tandem with a proper heat-setting of the fiber and/or yarn, it is not a requirement that all nucleating agents present within the target yarn and/or fiber exhibit a relatively high peak crystallization temperature. There are certain instances, however, wherein the nucleating agent does induce such high peak crystallization temperatures and thus their presence may be determined through differential scanning calorimetry analysis. For those nucleating agents that do not induce the target polymer to exhibit such high peak crystallization

28

temperatures, other methods of analysis (gas chromatography/mass spectroscopy, as one

example) may be utilized to determine their presence. For example, although sodium

benzoate is well known as a polyolefin nucleating agent (as defined above), peak

crystallization results within polypropylene yarns and/or fibers are not consistent with

accepted results for sodium benzoate within other types of polypropylene articles (such as

plaques, containers, and the like). Some peak crystallization measurements for sodium

benzoate within polypropylene fibers have been nearly as low as the measurements for the

polypropylene itself. Again, since sodium benzoate provides effective low-shrink

characteristics for such fibers and/or yarns, the lack of high peak crystallization

temperatures for such sodium benzoate-containing polypropylene fiber samples does not

remove sodium benzoate from the definition of nucleating agent for the purposes of this

invention.

Thus, for the polypropylene samples including the remaining types of nucleating

agents, peak crystallization was measured by the following method (a modified version of

ASTM D3417-99 including a manner of creating a proper measurable sample of the test

fibers themselves): A Perkin-Elmer DSC7 calibrated with an indium metal standard at a

heating rate of 20°C/min was used to measure the peak crystallization temperature of the

polypropylene fibers. Bundles of polypropylene fibers were heated to 220°C for 1 minute

and then compressed into thin disks approximately 250 ③m thick. The specific

polyolefin/DBS mixture composition was heated from 60°C to 220°C at a rate of 20°C per

minute to produce a molten formulation and held at the peak temperature for 2 minutes.

At that time, the temperature was then lowered at a rate of 20°C per minute until it reached

the starting temperature of 60°C. The peak crystallization temperature of the polymer was

29

thus measured as the peak maximum during the crystallization exotherm. This entire

procedure of first preparing fibers into plaques followed by DSC analysis in accordance

with the modified ASTM D-3417-99 test is herein referred to as "fiber peak crystallization

temperature measurement(s)" for the purposes of this invention. The results for the fiber

peak crystallization temperature measurements for the samples from Table 1, above, are

tabulated below (with a standard deviation of +/- 0.5°C):

EXPERIMENTAL TABLE 5
Peak Crystallization Temperatures For Yarn Samples

Sample Yarn	Heat-set Temp. (°C)	Peak Crystallization Temperature (Tc)(°C)
A	120	124.3
B	130	124.6
D	130	117.0
E	130	123.7
F	130	124.5
H	130	122.2
I(Comparative)	130	109.9

Thus, the presence of certain nucleating agents provided relatively high peak

crystallization temperatures for the sample yarns (at least above 115°C, and as high as a low

level of about 117.0°C).

Fabric Article Production and Analyses

Woven Fabric Comprising the Inventive Yarn

Fabric was woven using the inventive yarns and a 150 denier, 34 filament polyester

warp, and weaving a square weave with 84 picks/inch using five yarns: a control made as

above with no additive with final draw roll 3A and 3B temperatures of 110°C and 130°C.

Three experimental yarns were made having 2500 ppm 3,4-DMDBS (Sample yarns F,

from above) and a final draw roll 3A and 3B temperature of 110°C, 130°C, and 140°C

respectively. These sample fabrics were separated into 18 inch squares. A 12" box was

drawn in the center of the piece of fabric, and the fabric was washed five times in either

hot (60°C) or cold (20°C) water, and dried for 30 minutes in a conventional dryer (at about

70°C for 20 minutes). The dimensional change of the 12" box was measured, and is

reported in Table 6 as % shrinkage.

EXPERIMENTAL TABLE 6
Fabric Sample Shrinkage Data

Sample Fabric (corresponding to TABLE 1, above)	Yarn Heat-set Roll Temp. (°C)	Cold Wash Shrinkage	Hot Wash Shrinkage
F	110	2.4%	5.8%
F	130	2.9%	3.7%
F	140	2.4%	3.7%
I(Comparative)	110	8.9%	14.9%
I(Comparative)	130	5.0%	6.8%

Thus, it is evident that the fabric samples comprising the inventive yarns exhibit lower

shrinkage rates as well.

Knit Fabric Construction Comprising the Inventive Yarn

Yarns from TABLE 1 were produced with a heat-set roll temperature of 130°C and

were subsequently knit into socks on a Lawson Hemphill FAK Knitter 36 gage knitting

machine using 160 needles (needle no. 71.70) at speed setting 4 using 40 PSI of air

pressure. The fabric was laid flat, and a 2.75" x 10" section of sock was marked (10" in

the course direction, 2.75" in the wales direction). The socks were placed in an oven at

150°C (hot air) for five minutes, and then the dimensions of the marked section were

31

measured. The shrinkage in each direction and the area shrinkage are reported in TABLE

8, below. The area shrinkage is the product of the measured dimensions (the area) divided

by 27.5 sq. inches (the original area), reported as a percentage.

EXPERIMENTAL TABLE 7

150°C Hot Air Shrinkage Data For Knit Fabric Samples

Sample Yarn	Course Shrinkage	Wales Shrinkage	Area Shrinkage
A	5.3%	2.8%	8.0%
B	7.2%	2.8%	9.8%
C	8.8%	2.2%	10.8%
D	0.6%	3.4%	4.0%
E	1.6%	1.6%	3.2%
F	5.6%	2.8%	8.2%
H	7.2%	2.2%	9.2%
I(Comparative)	11.3%	4.4%	15.2%
Comm. Yarn 1	20.6%	5.3%	24.8%
Comm. Yarn 2	20.0%	3.8%	23.0%

Therefore, it is evident that the inventive knit fabrics exhibit far better shrinkage

characteristics than the commercial yarn-containing fabric samples as well as the control

without any nucleator compound present. The control yarn gave very high area shrinkage,

which was eclipsed by the air jet textured commercial yarns. Yarns with DBS and p-

MDBS gave very low shrinkage, easily acceptable within the apparel industry.

Non-Woven Fabric Construction Comprising the Inventive Yarn

Yarns from Sample E of TABLE 1 were produced with a heat-set roll temperature

of 130°C and were extruded at a pump rate of 87.6 cc/min with a 68 hole spinneret, to give

a total yarn denier of 680 and a denier per filament of 10. The fibers were combined by

plying such into 5 yarns of 2720 denier, which were then combined into a single tow of

13600 denier, which was heated at ~90°C in steam, crimped in a stuffer box, and then cut

32

to a staple length of 3.25 inches.   The staple was then carded, lapped using a Fiber Locker

manufactured by James Hunter Machine Company, and then needled with a Di-Lour-6

manufactured by Dilo, Inc. into a bat approximately 12 x 24 inches. Boxes of 130.3 cm^2

were marked on the bat. The bat was then molded by heating with an IR lamp for 60

seconds to temperatures reaching 120 - 150°C and then compressing in a 10°C mold. The

boxes showed average shrinkage of 3.2%.

A control yarn of 10 DPF with no additive was obtained. It was then crimped and

cut into staple, carded, lapped, and needled in the same manner. Boxes were again marked

prior to molding. When molded under the same conditions, the boxes showed an average

shrinkage of 11.7%.

It is thus evident that the non-woven fabrics made from the inventive low-shrink

propylene yarns also exhibit excellent low-shrink characteristics in comparison with

control samples.

There are, of course, many alternative embodiments and modifications of the

present invention which are intended to be included within the spirit and scope of the

following claims.

33